

Publication number: JP8196617

Publication date: 1996-08-06

Inventor: SHIKINAMI YASUO; IKADA  
YOSHITO; GEN JIYOUKOU;  
TSUTA KAORU; BOUYA  
HIDEKAZU

Applicant: TAKIRON CO; BIOMATERIAL  
UNIVERSE KK

Classification:

- international: **A61L27/00; A61L27/00**; (IPC1-7):  
A61L27/00

- European:

Application number: JP19950268999 19950925

Priority number(s): JP19950268999 19950925

[View INPADOC patent family](#)

[View list of citing documents](#)

[Report a data error here](#)

#### Abstract of **JP8196617**

PURPOSE: To provide a surgical material which has the same as bone or a little higher than that on compressive bending strength and compressive bending elastic modulus, by melt-molding a polylactic acid polymer having high molecular weight under a specified adjusted condition and drawing and cutting it. CONSTITUTION: This surgical material is an in vivo degradation absorbable material which is composed exclusively of a polylactic acid with viscosity average molecular weight of 300,000 to 600,000 or lactic acid-glycolic acid copolymer, thereby the surgical material having toughness and excellent hydrolysis-resistance is obtained by melt-molding these polymers and further cutting the drawn molding. On this occasion, the molding is cutting-worked into any shape of a plate, a pin, a machine screw, or a screw for bone conjugation. The compressive bending strength of the molding is  $1.6 \times 10^3$  kg/cm<sup>2</sup> or more, the compressive bending elastic modulus is  $5.0 \times 10^2$  kg/mm<sup>2</sup> or more, and the viscosity average molecular weight is 200,000 or more. Thereby, high compressive bending strength, the compressive bending elastic modulus and hydrolysis-resistance can be ensured.

---

Data supplied from the *esp@cenet* database - Worldwide